



Technical Data Sheet

RiKAFAST® P1
Sorbitol based clarifying agent for polypropylene

Product Description RiKAFAST P1 is a cost effective high performance sorbitol based clarifier for polypropylene homopolymer and random copolymer that imparts superior clarity and enhanced physical properties.

Chemical Name Main constituent 1:3,2:4 Di(methylbenzylidene) sorbitol

CAS Number 81541-12-0, 54686-97-4

Molecular Weight 386.5

Applications Conversion: Injection Moulding, Blow Moulding, Thermoforming
End product: Packaging, houseware articles, food containers, cups, bottles, trays

Features / Benefits RiKAFAST P1 is a cost effective improved version of 1,3:2,4-bis-O-(4-methylbenzylidene) sorbitol allowing the formulation of polypropylene compounds with superior organoleptic properties. In addition, RiKAFAST P1 utilises patented low melt technology allowing easier incorporation in the molten state during compounding. Increased crystallinity temperature also enables shorter moulding cycles.

Guidelines for use RiKAFAST P1 is used in concentration between 0.18% and 0.32% in polypropylene homopolymer and random copolymer.
Recommended processing temperature range: 190 - 240°C
Best suitable polymer: Polypropylene





Physical properties Physical form: White powder
Melting range: 200 - 220 °C
Bulk Density: 0.25 - 0.35 g/cm³

Handling & Safety In accordance with good industrial practice handle with care and prevent contamination of the environment.
Avoid dust formation and ignition sources.
For more detailed information, refer to the MSDS.

Registration RiKAFAST P1 is listed in the following inventories:
Europe: ELINCS / REACH Australia: AICS
USA: TSCA Korea: ECL
Japan: MITI China: IECSC
Canada: DSL & NDSL Philippine: PICCS

RiKAFAST P1 is approved in many countries for use in food contact applications. For detailed information contact our sales office.

Technical service information is issued as a guide to the properties and applications of the products of RiKA International Limited. We hope the information will be of use and, upon request we will be pleased to supplement it in any way possible. Every care is taken in compiling this information but we can assume no responsibility for any liability incurred, either in regard to results obtained or patent infringement.

